

**Product Data** 

# **Castrol Hysol SL 36 XBB**

High performance semi-synthetic metalworking fluid

## **Description**

Castrol<sup>®</sup> Hysol<sup>®</sup> SL 36 XBB is a high performance multimetal semi-synthetic metalworking fluid which is formulated without boron, biocides, formaldehyde releasing agents and chlorine. It contains an additive package that may help to enhance machining performance and surface finish, provide excellent product stability and lower the overall operations costs.

Castrol Hysol SL 36 XBB is suitable for large central systems and single sump machines.

### **Application**

Hysol SL 36 XBB is specifically designed for machining of cast iron and low-medium alloyed steel, but also suited for low to moderate duty machining of aluminum alloys.

ü ü suggested core application ü possible application, please consult Castrol representative prior to use

a a suggestion serie approacher a possible approacher, produce serieure exercit representant e prior to dec						
	Cast Iron	Low-medium alloyed steel	High alloyed - stainless steel	Aluminum alloys	Magnesium alloys	Yellow metals
Grinding	üü	üü	üü	ü		
Milling, Turning (general machining)	üü	üü	ü	ü		
Drilling	üü	üü	ü	ü		
Reaming, Tapping	üü	ü		ü		
Broaching	üü	ü				

## **Advantages**

- Formulated without boron, biocides, formladehyde releasing agents, chlorine and nitites which may help you to fulfill aspects of legislative and waste treatment requirements that specify that these chemicals are excluded
- Extend fluid life can help reduce maintenance and machine downtime
- Low foam in recommended water conditions (see details below)
- Excellent anti-corrosion properties to protect machine tools and parts
- Good wetting properties can help reduce coolant drag out and help deliver cleaner machine tools and components
- Suitable for a wide range of materials and applications provides opportunity for product consolidation

### **Typical Characteristics**

	Test Method	Unit	Value
<u>Concentrate</u>			
Appearance	Visual		Amber
Specific Gravity @ 15.6°C	CN-TM-084	g/cm <sup>3</sup>	0.965 - 0.985
<u>Emulsion</u>			
Appearance	Visual		translucent
pH in DI water (5%)	CN-TM-006		9.3
Refractometer Factor		BRIX unit multiplier	1.2

Subject to usual manufacturing tolerances.

#### **Recommended Concentrations**

Grinding 4-6% General Machining 5-10%

Water range 50-400 ppm CaCO<sub>3</sub>

#### Additional Information

	Boron	Formaldehyde releasing agent	EP-Ester	Amines	Chlorine
Additives			ü	ü	

### **Storage**

To avoid product deterioration always keep the container/drum tightly sealed. Store the product in a cool, dry place away from direct sunlight. Prevent exposure to frost and avoid water ingress. For optimum product stability, it is preferable to store the product indoors between 5°C and 45 °C / 41°F and 113°F.

For more details, please refer the product safety data sheet.

Castrol Hysol SL 36 XBB 06 Jan 2020

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.